

## Technical data sheet

# PLA+ WoodJet

Use	It is a material for the FDM (FFF) 3D printing additive technology.
Material	Poly lactid acid, Biodegradable material, Non petroleum product, Bamboo additive
Diameter	1,75 mm
Tolerance	± 0,1 mm
Weight	0,5 kg netto ± 5 % / 0,7 kg brutto ± 5 %
Packing	Spool in Vacuum ZIP bag, inserting to paper box, all in LDPE foil.
Colour	See <a href="http://www.filament-pm.com">www.filament-pm.com</a>
Solvents	1,2 Dichloroethane, Toluene, Tetrahydrofuran

Printing Properties	
Temperature HE	200 – 215 °C
Temperature HB	20 – 60°C
Surface bed	Kapton, Ultem, PET folie, běžně používané pro FDM tisk
Cooling print object	Yes
Nozzle	0,4 mm or bigger
Printer space	Open / Close

Material Properties			
Thermal	Vicat softening temperature	IISO 306	55 °C
	Heat deflection temperature	ISO 75	55 °C
Mechanical	Impact strength	ISO 179	10,2 kJ/m <sup>2</sup>
	Flexural modulus	ISO 178	53,1 MPa
Physical	Density	ISO 1183/B	1,19 g/cm <sup>3</sup>
	Melt Flow Index	ISO 1133	5 g/10 min



### Filament PM

Haňovice 18, 783 21 Czech republic

IČ: 00147346

tel. +420 585 100 308

e-mail: [info@filament-pm.com](mailto:info@filament-pm.com)

[www.filament-pm.com](http://www.filament-pm.com)

*Filament* 